

### PRODUCT DESCRIPTION

**SAKSHI CV 41** is a three pack epoxy base Finish coat, for coving of concrete Floor coating. **SAKSHI CV 41** is used as a finish coat of a coving system.

### PRINCIPAL CHARACTERISTICS

**SAKSHI CV 41** is a Coving finish Coat, to use over **SAKSHI CV 40**.

It has an excellent flow and leveling properties.

It has an excellent compressive strength and abrasion resistance.

Very good wearing and chemical resistance.

Excellent adhesion to concrete and masonry Substrates

Excellent impact resistant and flexibility.

High mechanical strength.

### BASIC DATA

Product density, g/cc	1.65±0.03
Recommended Dry Film Thickness	0.5-1 mm
Theoretical consumption	1.25±0.03 kg, for1 running meter.
Surface dry @ 30 °C	3 hours
Hard dry @ 30 °C	24 hours
Full Cure @ 30 °C	Min.7 days
Pot Life@ 30 °C	45 min.
Compressive strength	>80 N/ mm <sup>2</sup> as per IS 9162
Flexural strength	>40 N / mm <sup>2</sup>
Adhesion	>1.50 N / mm <sup>2</sup>
Corrosion Resistance	Excellent
Flame resistance	Self Extinguishing, Flame Retardant

### Instructions for use:

**Surface Preparation:** A clean, dry and sound, concrete substrate is essential for Floor coating application and in ensuring maximum bonding between the substrate and flooring system. New concrete surface must be a minimum of 30 days old, free from curing Compounds and have moisture content less than 3-4 % prior to application of the primer.

The surface can be prepared mechanically using shot blasting or other blasting equipment, or by acid etching followed by thorough water wash and wire brushing.

The choice of surface preparation should be determined by the extent and nature of contamination present on the concrete surface. All dust present must be removed prior to coving coat application.

### **Mixing Ratio – 2.00:1.00:10.00 (BASE: HARDENER: FILLER)**

**Mixing:** Stir the base and hardener separately, with the help of power driven hand stirrer, mix hardener into the base. Then add filler in that mixture as per the stated mixing ratio

Apply after induction time and before expiration of pot life.

**Application:** This coat can be applied on primed Substrate temperature should be at least 3 °C above dew point.

Maximum relative humidity during application and curing is below 85%

All tools and equipment can be cleaned with Thinner SAKSHI THINNER 400.

Coving coat application must be done when the previous coat to be dry .

Allow to cure for overnight.

### Storage & Packing

Storage: Store in a cool, dry place.

Packing: 10, 20 Kgs

### Shelf life

12 Months (cool & dry place)

### Safety Information

As a general safety measure, inhalation of solvent vapors or coating mist and contact of coating with skin & eyes should be avoided. Forced ventilation should be provided when applying coating in Confined spaces or stagnant air. Even when ventilation is provided, respiratory, skin and eye Protections are always recommended while coating application.

---

### LIMITATION OF LIABILITY

The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by SAKSHI COATING PVT LTD, whether in technical documentation or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. The products and information are designed for users having requisite knowledge and industrial skills and it is the end-user's responsibility to determine the suitability of the product for its intended use. SAKSHI COATING PVT LTD has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. SAKSHI COATING PVT LTD does therefore not accept any liability arising from loss, damage or injury resulting from such use or the contents of this data sheet. **Date-JAN. 2019**

---

